









Hodnocení podkorodování nátěrů

Stupeň prorezavění				Rozsah korozního poškození (%)	Zobrazení (orientační)
ISO 4628/3	ČSN 03 8139	ČSN 67 3088	ASTM D 610		
Ri 0	1	0	10	0	
Ri 1	2	1	7,5-9,0	0,05	0,1% 
Ri 2		2	6,75-7,5	0,5	0,5% 
Ri 3		3	6,0-6,75	0,5 – 1,0	1% 
	3	4	5,25-6,0	1,0 - 2,5	3% 
	4	5	4,75-5,25	2,5 - 5,0	5% 
Ri 4	5		4,0-4,75	8	
		6		10	10% 
		7	2,45-4,0	25	20% 
		8	1,0-2,45	40/50	30% 
Ri 5		9	0	>50	